

Test Report No.: 68.404.22.9036.01

Dated: 2022-06-06



Applicant : Suichang Chenyang Tourism Products., Ltd
No.91,Lianxi East Road,Shilian Industrial area,Suichang
County,Zhejiang

Sample Description : BLUE/WHITE STRIPE LINING

Style No. / Name / Design No. : North sea model#1015846

PO No. / Order No. : PO-22-21974 / PO-22-21975

Country of Origin : China

Exported to : Europe

Test Sample Receipt Date, Location : 2022-05-23, Shenzhen

Test Period, Location : From 2022-05-23 to 2022-05-30, Shenzhen

Test Result(s) : Refer to Section 3





Purpose Of Examination / Conclusion:

No.	Test Item(s)	Conclusion
1.	Azodyes Regulation (EC) No. 1907/2006, Regulation (EC) No. 552/2009 Annex XVII Entry 43 and its amendment Regulation (EU) 2020/2096	Pass

Remarks:

- (1) The results relate only to the items tested.
- (2) Samples are tested as received.
- (3) "Pass" means the measured result is within a limit, even when extended by expanded uncertainty. "Fail" means the measured result is beyond a limit, even when extended by expanded uncertainty. "Inconclusive" means the measured result can be within or beyond a limit when extended by expanded uncertainty. The confidence level of the expanded uncertainty for "Pass", "Fail" and "Inconclusive" is 95%.

TüV Süd Certification and Testing (China) Co., Ltd. Shenzhen Branch
TüV Süd Group

Prepared by:

Reviewed by:



Hailey Tan
Project Engineer

Samson Ye
Senior Project Engineer

Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production. For further details, please see testing and certification regulation, chapter A-3.4.

Test Report No.: 68.404.22.9036.01


Dated: 2022-06-06



1. Description of the Test Sample:

Sample Description	BLUE/WHITE STRIPE LINING
--------------------	--------------------------

2. List of Materials as identified by the Laboratory:

T. No.	Sample No.	Colour and Description	Photograph
T1	001	Dark blue / white fabric	



3. Test Results

3.1 Azodyes

Regulation (EC) No. 1907/2006, Regulation (EC) No. 552/2009 Annex XVII Entry 43 and its amendment
Regulation (EU) 2020/2096

Test in accordance with EN ISO 14362-1:2017 (for textiles) or ISO 17234-1:2015 (for leather).

The presence of 4-aminoazobenzene is determined by EN ISO 14362-3:2017 or ISO 17234-2:2011.

[Reporting Limit = 5.0 mg/kg]

No.	Forbidden Amine	CAS No.	Results [mg/kg]
			Sample 001
1	4-aminobiphenyl	92-67-1	<5.0
2	Benzidine	92-87-5	<5.0
3	4-chloro-o-toluidine	95-69-2	<5.0
4	2-naphthylamine	91-59-8	<5.0
5	o-aminoazotoluene	97-56-3	<5.0
6	5-nitro-o-toluidine	99-55-8	<5.0
7	4-chloroaniline	106-47-8	<5.0
8	2,4-diaminoanisole	615-05-4	<5.0
9	4,4'-diaminodiphenylmethane	101-77-9	<5.0
10	3,3'-dichlorobenzidine	91-94-1	<5.0
11	3,3'-Dimethoxybenzidine	119-90-4	<5.0
12	3,3'-dimethylbenzidine	119-93-7	<5.0
13	4,4'-methylenedi-o-toluidine	838-88-0	<5.0
14	p-cresidine	120-71-8	<5.0
15	4,4'-methylene-bis-(2-chloro-aniline)	101-14-4	<5.0
16	4,4'-oxydianiline	101-80-4	<5.0
17	4,4'-thiodianiline	139-65-1	<5.0
18	o-toluidine	95-53-4	<5.0
19	2,4-toluenediamine	95-80-7	<5.0
20	2,4,5-trimethylaniline	137-17-7	<5.0
21	2-methoxyaniline	90-04-0	<5.0
22	2,4-xylydine	95-68-1	<5.0
23	2,6-xylydine	87-62-7	<5.0
24	4-aminoazobenzene	60-09-3	<5.0
Method			EN ISO 14362-1:2017(P1) EN ISO 14362-1:2017(P2)
Limit			<30 mg/kg
Conclusion			Pass

Note:

1. “#” denotes 2,4-xylydine and 2,6-xylydine are not under Regulation (EC) No.1907/2006 and they are for client’s reference.
2. “<” denotes less than
3. “mg/kg” denotes milligram per kilogram

* Azo colorants that are able to form 4-aminoazobenzene, as generated under the current testing condition stated in EN ISO 14362-1:2017 are aniline and 1,4-phenylenediamine. The presence of 4-aminoazobenzene is determined by EN ISO 14362-3:2017 or ISO 17234-2:2011.

Interpretation of test results:

- (1) In the case of the measured value per amine component ≤ 30 mg/kg and according to the analysis carried out, the azo colourants banned under the Annex XVII of Regulation (EC) No. 1907/2006, REACH are not detected in the article submitted.
- (2) In the case of the measured value per amine component > 30 mg/kg, the analysis result suggests that the submitted article was manufactured or treated with the azo colourants banned under Annex XVII of Regulation (EC) No. 1907/2006, REACH
- (3) In the case of the measured value per amine component being between 25 and 35 mg/kg, it is remarked that due to the inherent uncertainty of the detection method, the value represent a border line case.

-- END OF THE TEST REPORT --